

Robur Flash UKP

Pulp characteristics

Property	Standard	Unit	Drainage resistance °SR				
			13	15	20	25	30
Beating energy, PFI	ISO 5267-1	Rev.	400	2600	6500	8700	11100
Density	ISO 534	kg/m ³	600	680	730	750	760
Bulk	ISO 534	cm ³ /g	1.7	1.5	1.4	1.3	1.3
Tensile index	ISO 1924-3	kNm/kg	35	78	100	104	107
Tear index	ISO 1974	Nm ² /kg	20	15	12	11	11
Burst index	ISO 2758	MN/kg	2,9	5,6	7.4	7.9	8.0
Air permeability, Gurley	ISO 5636-5	mm/kPa s	100	52	19	9	5

Property	Unit	Standard	Standard
Brightness	% ISO	25	ISO 2469
Intrinsic viscosity	ml/g	1250	ISO 5351
Kappa no		27	ISO 302
Ash	%	0.3	ISO 1762
Extractives (acetone)	%	< 0.05	ISO 14453

Testing climate: 50% RH, temp: 23 °C

Additional comments: All values are nominal.



Certificates

Chain of custody/Controlled wood	Available on request
Conformity with food contact materials	Isega
EU Ecolable	Approved pulp for EU Ecolable
Nordic Ecolabel	Approved pulp for Nordic Ecolabel



Robur Flash UKP

Packaging information

		Bales (LxWxH)	Units (LxWxH)
Number of bales			8
Gross weight	kg	200	1600
Dry content	%		89
Size (H = avg height)	cm	90x60x40	90x120x160
Number of wires		0	7
Wrapping		Unbleached Kraft paper	

General information

Wood species:	Spruce and Pine
Digester type:	Continuous
Drying	Flash dried
Producing mill	Vallvik

